



# Random Copolymer 1200

## Product Description

Random Copolymer Polypropylene –  
Injection - Clarified

| Properties                   | Property Value | Test Method |
|------------------------------|----------------|-------------|
| Melt Index (g/10 min)        | 12             | ASTM D1238  |
| Izod (ft-lbs./in)            | 1              | ASTM D256   |
| Flexural Modulus (psi)       | 150,000        | ASTM D790   |
| Tensile Strength Yield (psi) | 3,800          | ASTM D638   |
| Elongation @ Break (%)       | 10             | ASTM D638   |

\* These average values were obtained from specimens molded under carefully controlled conditions in a laboratory. This data should be used only as a guide and no assurance can be offered by the company that all molded articles will exhibit exact properties at those listed above.

The information contained herein is based on our best knowledge and we believe it to be true and accurate. Please read all statements and recommendations in conjunction with our conditions of sale, which apply, to all goods supplied by Stewart Polymer Solutions. Statements concerning possible uses of materials described wherein are not to be construed as recommendations for use of such materials in the infringement of any patent or copyright. The user of this material must make their own evaluations to determine the suitability of this material from a technical as well as a health, safety and environment/ standpoint. This data is not intended for specification purposes.